

TECHNICAL DATA SHEET

TENCOVER METAL FREE 3PLY DISPOSABLE MEDICAL MASKS ASTM LEVEL 3

Intended Use: Level 3 masks are intended protect and reduce the risk of transfer of micro organisms, body fluids and particulate material transfer

Testing Standard: As per ASTM F2100-19

| Characteristic | Level 3 |
|--|---------|
| Bacterial Filtration Efficiency, % | ≥98 |
| Differential Pressure, mm H ₂ O/cm ₂ | <6.0 |
| Sub-Micron Particulate Filtration Efficiency | ≥98 |
| Synthetic Blood Penetration | 160 |
| Flame Spread | Class 1 |

| Mask Construction | <u>Material</u> |
|---------------------------|---------------------------------|
| Outer Layer | Spun bond polypropylene |
| Middle Layer (Filtration) | BFE 99 Melt blown polypropylene |
| Inner Layer | Spun bond polypropylene |
| Nose Piece | 100% Polypropylene |
| Ear Loop | Spandex & Nylon |